



Specializing in Research & Development of High Performance Pressure Sensitive Tapes

Product Data Sheet DC-3075

Product Description: Product DC-3075 is a random glass fiber supported very high tack and peel acrylic transfer film. DC-3075 exhibits excellent dead load shear properties at RT as well as moderately elevated temperature, along with having excellent cold resistance. This product is intended for use on ether and ester urethane foams, and other difficult to adhere to surfaces including low surface energy plastics.

Physical Characteristics	Nominal Values
Total Tape Thickness	5 mils
Liner Type	76 # Polycoated
Liner Thickness	.0055"
Peel Adhesion (PSTC-1)	129 oz/in
Loop Tack	89 oz/sq. in.
Holding Power (PSTC-7) 1" x 1" x 1000g	> 180 hrs
Standard Length	60 yds

Tape Application: To achieve ultimate bond strength please be sure materials being bonded are clean and free of dust, dirt, oil or other substances which can affect the bond of the tape adhesive. Firm application pressure will promote a strong, long lasting bond. Adhesive bond strength is dependent upon the material type being bonded. If a variety of materials are being used, please be sure to test the suitability of product performance with each material. Please contact Custom Adhesive Products at the phone number below with questions regarding your taping applications and needs.

Notice: Physical and performance values listed above are average values obtained from tests performed according to PSTC or ASTM standard test methods. Custom Adhesive Products does not make any warrant of any kind as to the results listed above. The information listed above does not represent a performance guarantee. Product performance may vary with each individual application and the purchaser should test the product prior to use and satisfy themselves regarding product functionality in their application. Custom Adhesive Products shall not be liable for damages in excess of the purchase price of its products or for incidental or consequential damages.